



Cimar[®]
produzione s.u.r.l.

Via Mecio Gracco 8H/I - 84131 Salerno IT
Tel/Fax +39 089 302418 - info@cimarproduzione.com
www.cimarproduzione.com

BLACKKOTE GOLD (waterproofing bituminous paste)

technical data sheet

BLACKKOTE GOLD (waterproofing bituminous paste.)

revision date 18.10.19

1. IDENTIFICATION OF THE SUBSTANCE/COMPANY

Trade name: BLACKKOTE GOLD (waterproofing bituminous paste)
Manufacturer : Cimar Produzione Surl with plant in Salerno at via Mecio Gracco 8H/8I.
Telephone number also for urgent calls: Tel +39 089.302418

2. CHARACTERISTICS AND USES

BLACKKOTE GOLD is a bituminous waterproofing paste for universal use.
The economical version of its big brother EXTRALARGE, it can be used as waterproofing for any type of support, both horizontally and vertically and for gluing insulating panels.
It is a water-based product.
Resists waterlogging.

3. IDENTIFICATION CHARACTERISTICS OF THE LIQUID PRODUCT

It is a thixotropic paste, impalpable and dark in colour, dilutable in water.
It dries quickly forming a glossy film with the characteristic of presenting high impermeability even in the presence of strong water stagnations.
Specific gravity = $1.2 \pm 0.05 \text{ kg/dm}^3$
Dry residue = $70 \pm 1\%$
Viscosity at 23°C* = thixotropic gel
VOC content as required by Legislative Decree No. 161 of 27/05/2006: 140 g/l of product ready for use.
VOC content of the product: 10 g/l of ready-to-use product

4. DRYING OR HARDENING TO 23°C AND 50% UR

Surface: 40 '
To the touch: 2 hours
Apparent complete: 6 hours

5. CHARACTERISTICS OF THE DRIED PRODUCT

Elongation at break: 300% Cold flexibility: -10 °C

6. EQUIPMENT

Apply by roller, brush or airless spray. The equipment can be cleaned immediately after working with water, otherwise with mineral spirit.

7. APPLICATION SUPPORT

BLACKkOTE GOLD must be applied on clean surfaces, free from dust and without friable parts. For porous substrates we recommend applying a bituminous primer, solvent or water-based, ready to use. After the primer has dried, the two waterproofing layers of BLACKkOTE GOLD will be applied with a total consumption of 2 Kg/sqm. It is advisable to place our POTENZIO TNT between one hand and the other.

8. CONSUMPTION

Consumption is a function of the porosity and regularity of the surface to be treated; however, it can be estimated in 1 Kg/sq.m. per coat; two coats recommended.

9. INSTRUCTIONS FOR STORAGE

Storage temperature: 5°C ÷ 30°C
Stability in original packages : 12 months
Packing : 5 Kg-10 Kg -18 Kg. The product is frost sensitive.

10. WARNINGS

Avoid applying the product on surfaces where water stagnation or damp surfaces may occur.
Apply the product at higher temperatures +10°C.
Do not apply in case of imminent rain, dew, mist.

The information contained in this brochure is, to the best of our knowledge, accurate and correct, but any recommendation or suggestion given is without any guarantee, as the conditions of use are not under our direct control. In case of doubt it is always advisable to carry out preliminary tests and/or ask for the intervention of our technicians. The company Cimar Produzione srl reserves the right to modify, replace and / or delete the articles, and change the data of the products shown in this brochure, without notice, in which case the information contained herein may no longer be valid.